



Technical data for Gibo Plast A/S **ABS/PMMA** [CAS: 9003-56-9](#)

Listed data is the minimum requirements for the all products in that specific kategori, ABS/ACRYL 20, ABS/ACRYL 30 and ABS/ACRYL 35, unless marked with (Max). Data with a tolerance is marked by(±X%). All products are extruded.

**GENERAL**

Property	Method	Unit	ABS/ACRYL 20	ABS/ACRYL 30	ABS/ACRYL 35
Density (±2,5%)	ISO 1183	g/cm <sup>3</sup>	1.07	1.10	1.09
Water absorption (Max)	DIN EN ISO 62 Method 1	%	-	0.30	-
Ball indentation hardness	ISO 2039-1	MPa	-	-	-
Flammability	UL 94	-	HB	HB	HB

**MECHANICAL**

Property	Method	Unit	ABS/ACRYL 20	ABS/ACRYL 30	ABS/ACRYL 35
Tensile strength	ISO 527-2	MPa	33	-	-
Elongation at break	ISO 527-2	%	7	-	-
Tensile modulus	ISO 527-2	MPa	1900	1800	1700
Flexural strength	ISO 178	MPa	-	-	-
Flexural modulus	ISO 178	MPa	-	-	-
Yield Stress	ISO 527-1	Mpa	36	34	34
<b>Impact strength @23 °C (Charpy unnotched)</b>	<b>ISO 179</b>	<b>KJ/m<sup>2</sup></b>	<b>20</b>	<b>30</b>	<b>35</b>
Impact strength @23°C (Charpy notched)	ISO 179	KJ/m <sup>2</sup>	10	10	10

**THERMAL**

Property	Method	Unit	ABS/ACRYL 20	ABS/ACRYL 30	ABS/ACRYL 35
Vicat temperature (B 50) (±1%)	ISO 306B	°C	94	94	94
HDT-A (@1.8 Mpa) (±1%)	ISO 75	°C	89	89	89
Service temperature (Continuous use)	-	°C	85	85	85
Max. temperature (Short term use)	-	°C	100	100	100

Gibo Plast A/S | Ferrodanvej 14 | DK-6900 Skjern | Tlf: +45 8782 8700 | Fax: +45 8725 1110 | E-mail: [post@giboplast.com](mailto:post@giboplast.com)

The technical data have been collected and categorised by Gibo Plast A/S in good faith. They are non-binding and do not represent a material specification or assurance of specific properties. We explicit reserve the right to change or update these instructions at any time.

Further processing and use of the products can have various impact on the products. Therefore, Gibo Plast A/S, does not guarantee or warrant for the fitness, suitability or adequacy of the products for any purpose intended by the purchaser or any third person and shall have no liability whatsoever in this respect. The purchaser has the obligation to test the products and determine itself is the products are fit for the intended use.

Gibo Plast A/S shall neither nor indirectly, indemnify and hold harmless purchaser or any third person in the event of any third-party claims related to the infringement of intellectual property rights.